

Release Date: 3/12/2011

				Overall Compression				Cover Hardness	
				Majestix		Atti		Teclock Type C	
	Manufacturer	Model	Year	Avg	MPI™	Avg	MPI™	Avg	MPI™
1	Bridgestone	e5 (06)	2006	99	80	103	85	78	88
2	Bridgestone	e5+ (07)	2007	97	78	95	77	79	89
3	Bridgestone	e6 (06)	2006	70	51	76	58	85	95
4	Bridgestone	e6 (10)	2010	71	49	73	52	85	95
5	Bridgestone	e6+ (07)	2007	74	55	73	55	85	95
6	Bridgestone	e7+ (09)	2009	106	87	102	84	86	96
7	Bridgestone	Tour B330 (06)	2006	111	92	116	98	82	92
8	Bridgestone	Tour B330 (07)	2007	110	91	115	97	80	90
9	Bridgestone	Tour B330 (08)	2008	111	89	110	89	81	91
10	Bridgestone	Tour B330 (09)	2009	111	92	107	89	82	92
11	Bridgestone	Tour B330-RX (08)	2008	90	68	91	70	80	90
12	Bridgestone	Tour B330-RX (09)	2009	90	71	86	68	81	91
13	Bridgestone	Tour B330-RXS (10)	2010	78	56	79	58	74	84
14	Bridgestone	Tour B330-S (06)	2006	96	77	99	81	80	90
15	Bridgestone	Tour B330-S (07)	2007	101	82	109	91	81	91
16	Bridgestone	Tour B330-S (09)	2009	104	85	97	79	79	89
17	Bridgestone	e5 (10)	2010	103	81	103	82	79	89
18	Bridgestone	e7 (10)	2010	103	81	104	83	88	98
19	Bridgestone	Tour B330-S (08)	2008	104	82	105	84	76	86
20	Callaway	Big Bertha (06)	2006	84	65	84	66	85	95
21	Callaway	HX Hot (06)	2006	91	72	97	79	88	98
22	Callaway	HX Hot (07)	2007	99	80	99	81	88	98
23	Callaway	HX Hot Bite (08)	2008	104	85	104	86	83	93
24	Callaway	HX Hot Plus (09)	2009	86	64	88	67	86	96
25	Callaway	HX Pearl (07)	2007	95	76	94	76	87	97
26	Callaway	HX Tour (06)	2006	112	93	115	97	88	98
27	Callaway	HX Tour 56 (06)	2006	101	82	108	90	86	96
28	Callaway	Tour i (08)	2008	109	90	104	86	84	94
29	Callaway	Tour i(s) (10)	2010	98	76	100	79	83	93
30	Callaway	Tour i(z) (10)	2010	119	97	118	97	85	95
31	Callaway	Tour ix (08)	2008	111	92	107	89	86	96
32	Callaway	Big Bertha Diablo (09)	2009	66	44	66	45	79	89
33	Callaway	HX Hot Bite (09)	2009	113	91	113	92	82	92
34	Callaway	Solaire (09)	2009	76	54	77	56	86	96
35	Dixon	Earth (09)	2009	94	72	99	78	87	97
36	Maxfli	BlackMax (06)	2006	114	95	107	89	80	90
37	Maxfli	Fire (07)	2007	98	79	98	80	89	99
38	Maxfli	Noodle Long & Soft (07)	2007	90	71	98	80	88	98
39	Maxfli	RedMax (06)	2006	90	71	95	77	82	92
40	Nike	Crush (10)	2010	86	64	90	69	84	94
41	Nike	Ignite (06)	2006	86	67	88	70	78	88
42	Nike	Ignite (07)	2007	87	68	89	71	87	97
43	Nike	One Black (06)	2006	109	90	102	84	78	88
44	Nike	One Black (07)	2007	102	83	101	83	80	90
45	Nike	One Black (08)	2008	100	81	97	79	80	90
46	Nike	One Platinum (06)	2006	97	78	102	84	77	87
47	Nike	One Platinum (07)	2007	101	82	102	84	76	86
48	Nike	One Platinum (08)	2008	107	88	105	87	77	87
49	Nike	One Tour (09)	2009	113	94	108	90	77	87
50	Nike	One Tour D (09)	2009	100	81	99	81	81	91
51	Nike	One Vapor (09)	2009	85	63	88	67	85	95
52	Nike	One Vapor Speed (10)	2010	85	63	84	63	85	95
53	Nike	Power Distance Soft (10)	2010	79	57	78	57	82	92

Release Date: 3/12/2011

				Overall Compression						Cover Hardness	
				Majestix		Atti		Teclock Type C			
	Manufacturer	Model	Year	Avg	MPI™	Avg	MPI™	Avg	MPI™		
54	Nike	Vapor (09)	2009	83	<b>64</b>	83	<b>65</b>	85	<b>95</b>		
55	Nike	Power Distance Soft (08)	2008	70	<b>51</b>	74	<b>56</b>	84	<b>94</b>		
56	Noodle	Noodle + (08)	2008	75	<b>56</b>	78	<b>60</b>	86	<b>96</b>		
57	Noodle	Noodle+ Easy Dist (10)	2010	60	<b>38</b>	61	<b>40</b>	81	<b>91</b>		
58	Pinnacle	Exception (07)	2007	78	<b>59</b>	79	<b>61</b>	86	<b>96</b>		
59	Pinnacle	Platinum Distance (08)	2008	85	<b>66</b>	86	<b>68</b>	87	<b>97</b>		
60	Pinnacle	Platinum Feel (08)	2008	81	<b>62</b>	80	<b>62</b>	83	<b>93</b>		
61	Pinnacle	Ribbon (08)	2008	86	<b>67</b>	88	<b>70</b>	88	<b>98</b>		
62	Pinnacle	Dimension (09)	2009	86	<b>64</b>	90	<b>69</b>	83	<b>93</b>		
63	Pinnacle	Gold Distance (09)	2009	91	<b>69</b>	96	<b>75</b>	88	<b>98</b>		
64	Precept	Distance IQ 180 (08)	2008	70	<b>51</b>	78	<b>60</b>	86	<b>96</b>		
65	Precept	Lady IQ 180 (08)	2008	67	<b>48</b>	68	<b>50</b>	86	<b>96</b>		
66	Precept	Lady IQ Plus (09)	2009	60	<b>38</b>	67	<b>46</b>	85	<b>95</b>		
67	Srixon	AD-333 (06)	2006	82	<b>63</b>	86	<b>68</b>	81	<b>91</b>		
68	Srixon	AD-333 (07)	2007	78	<b>59</b>	78	<b>60</b>	83	<b>93</b>		
69	Srixon	Soft Feel (06)	2006	75	<b>56</b>	81	<b>63</b>	85	<b>95</b>		
70	Srixon	Soft Feel for Ladies (08)	2008	75	<b>56</b>	75	<b>57</b>	87	<b>97</b>		
71	Srixon	Tri-Speed (07)	2007	69	<b>50</b>	73	<b>55</b>	85	<b>95</b>		
72	Srixon	Z Star X (09)	2009	106	<b>87</b>	103	<b>85</b>	81	<b>91</b>		
73	Srixon	Z-Star (09)	2009	90	<b>71</b>	88	<b>70</b>	81	<b>91</b>		
74	Srixon	Z-UR (06)	2006	110	<b>91</b>	111	<b>93</b>	85	<b>95</b>		
75	Srixon	Z-URC (07)	2007	110	<b>91</b>	102	<b>84</b>	85	<b>95</b>		
76	Srixon	Z-URS (06)	2006	100	<b>81</b>	102	<b>84</b>	83	<b>93</b>		
77	Srixon	Z-URS (07)	2007	98	<b>79</b>	95	<b>77</b>	81	<b>91</b>		
78	Srixon	AD-333 (09)	2009	77	<b>55</b>	81	<b>60</b>	83	<b>93</b>		
79	Srixon	Z Star (09)	2009	91	<b>69</b>	92	<b>71</b>	81	<b>91</b>		
80	Srixon	Z Star X (09)	2009	105	<b>83</b>	108	<b>87</b>	82	<b>92</b>		
81	TaylorMade	Burner (08)	2008	77	<b>58</b>	73	<b>55</b>	86	<b>96</b>		
82	TaylorMade	Burner (10)	2010	76	<b>54</b>	76	<b>55</b>	90	<b>100</b>		
83	TaylorMade	Burner Tour (10)	2010	75	<b>53</b>	76	<b>55</b>	79	<b>89</b>		
84	TaylorMade	Burner TP (08)	2008	87	<b>68</b>	89	<b>71</b>	81	<b>91</b>		
85	TaylorMade	Penta TP (10)	2010	103	<b>81</b>	101	<b>80</b>	76	<b>86</b>		
86	TaylorMade	TP Black (06)	2006	117	<b>98</b>	110	<b>92</b>	82	<b>92</b>		
87	TaylorMade	TP Black (08)	2008	117	<b>98</b>	115	<b>97</b>	80	<b>90</b>		
88	TaylorMade	TP Red (06)	2006	111	<b>92</b>	106	<b>88</b>	81	<b>91</b>		
89	TaylorMade	TP Red (08)	2008	95	<b>76</b>	92	<b>74</b>	80	<b>90</b>		
90	Titleist	DT Carry (08)	2008	79	<b>60</b>	79	<b>61</b>	80	<b>90</b>		
91	Titleist	DT Roll (08)	2008	87	<b>68</b>	90	<b>72</b>	83	<b>93</b>		
92	Titleist	DT SoLo (06)	2006	79	<b>60</b>	78	<b>60</b>	84	<b>94</b>		
93	Titleist	DT SoLo (10)	2010	83	<b>61</b>	84	<b>63</b>	86	<b>96</b>		
94	Titleist	NXT (06)	2006	73	<b>54</b>	77	<b>59</b>	88	<b>98</b>		
95	Titleist	NXT (10)	2010	82	<b>60</b>	85	<b>64</b>	88	<b>98</b>		
96	Titleist	NXT Extreme (07)	2007	76	<b>57</b>	82	<b>64</b>	88	<b>98</b>		
97	Titleist	NXT Tour (06)	2006	88	<b>69</b>	88	<b>70</b>	80	<b>90</b>		
98	Titleist	NXT Tour (07)	2007	88	<b>69</b>	92	<b>74</b>	81	<b>91</b>		
99	Titleist	NXT Tour (10)	2010	96	<b>74</b>	96	<b>75</b>	85	<b>95</b>		
100	Titleist	Pro V1 (06)	2006	97	<b>78</b>	99	<b>81</b>	76	<b>86</b>		
101	Titleist	Pro V1 (07)	2007	93	<b>74</b>	95	<b>77</b>	78	<b>88</b>		
102	Titleist	Pro V1 (09)	2009	95	<b>76</b>	98	<b>80</b>	78	<b>88</b>		
103	Titleist	Pro V1x (06)	2006	110	<b>91</b>	114	<b>96</b>	78	<b>88</b>		
104	Titleist	Pro V1x (07)	2007	103	<b>84</b>	100	<b>82</b>	79	<b>89</b>		
105	Titleist	Pro V1x (09)	2009	104	<b>85</b>	104	<b>86</b>	79	<b>89</b>		
106	Top Flite	D2 Feel (07)	2007	71	<b>52</b>	74	<b>56</b>	85	<b>95</b>		

Release Date: 3/12/2011

				Overall Compression				Cover Hardness	
				Majestix		Atti		Teclock Type C	
	Manufacturer	Model	Year	Avg	MPI™	Avg	MPI™	Avg	MPI™
107	Top Flite	D2 Straight (07)	2007	77	<b>58</b>	77	<b>59</b>	87	<b>97</b>
108	Top-Flite	Freak (08)	2008	87	<b>68</b>	88	<b>70</b>	90	<b>100</b>
109	Top-Flite	Gamer (08)	2008	98	<b>79</b>	95	<b>77</b>	83	<b>93</b>
110	Top-Flite	Gamer V2 (10)	2010	85	<b>63</b>	91	<b>70</b>	83	<b>93</b>
111	Volvik	PROs Pect (07)	2007	81	<b>62</b>	81	<b>63</b>	86	<b>96</b>
112	Wilson	C:25 (10)	2010	85	<b>63</b>	88	<b>67</b>	90	<b>100</b>
113	Wilson	D:25 (10)	2010	66	<b>44</b>	69	<b>48</b>	88	<b>98</b>
114	Wilson	DX2 Distance (06)	2006	85	<b>66</b>	83	<b>65</b>	85	<b>95</b>
115	Wilson	Fifty (07)	2007	75	<b>56</b>	72	<b>54</b>	83	<b>93</b>
116	Wilson	PX3 Performance (06)	2006	80	<b>61</b>	84	<b>66</b>	82	<b>92</b>
117	Wilson	TX4 Pro (08)	2008	119	<b>100</b>	118	<b>100</b>	84	<b>94</b>
118	Wilson	TX4 Tour (06)	2006	109	<b>90</b>	105	<b>87</b>	82	<b>92</b>
119	Wilson	Zip (07)	2007	68	<b>49</b>	67	<b>49</b>	83	<b>93</b>
120	Wilson	FG Tour (10)	2010	93	<b>71</b>	92	<b>71</b>	76	<b>86</b>
121	Wilson	Hope (07)	2007	81	<b>62</b>	84	<b>66</b>	88	<b>98</b>

**Technical Notes:**

1. Compression tests performed measuring overall golf ball compression using the Majestix and Atti compression test devices. The higher the number, the less the ball compresses when subjected to a force.
2. Cover hardness tests performed measuring golf ball surface hardness using a Teclock Type C durometer test device in accordance with ASTM D 2240 C.