



**Compression and Cover
Hardness Ratings**

MPI™ Data Sheet

Release Date: 4/19/2008

				Overall Compression				Cover Hardness			
				Majestix		Atti		Teclock Type C			
	Manufacturer	Model	Year	Avg	MPI™	Avg	MPI™	Avg	MPI™	Avg	MPI™
1	Bridgestone	Tour B330 (07)	2007	110	91	115	97	80	90		
2	Bridgestone	Tour B330S (07)	2007	101	82	109	91	81	91		
3	Bridgestone	Tour B330 (06)	2006	111	92	116	98	82	92		
4	Bridgestone	Tour B330S (06)	2006	96	77	99	81	80	90		
5	Bridgestone	e5+ (07)	2007	97	78	95	77	79	89		
6	Bridgestone	e6+ (07)	2007	74	55	73	55	85	95		
7	Bridgestone	e5 (06)	2006	99	80	103	85	78	88		
8	Bridgestone	e6 (06)	2006	70	51	76	58	85	95		
9	Callaway	Big Bertha (06)	2006	84	65	84	66	85	95		
10	Callaway	HX Tour (06)	2006	112	93	115	97	88	98		
11	Callaway	HX Tour 56 (06)	2006	101	82	108	90	86	96		
12	Callaway	HX Hot (07)	2007	99	80	99	81	88	98		
13	Callaway	HX Hot (06)	2006	91	72	97	79	88	98		
14	Callaway	HX Hot Bite (08)	2008	104	85	104	86	83	93		
15	Callaway	HX Pearl (08)	2008	95	76	94	76	87	97		
16	Callaway	Tour ix (08)	2008	111	92	107	89	86	96		
17	Maxfli	Fire (07)	2007	98	79	98	80	89	99		
18	Maxfli	Noodle Long & Soft (06)	2006	90	71	98	80	88	98		
19	Maxfli	BlackMax (06)	2006	114	95	107	89	80	90	G	
20	Maxfli	RedMax (06)	2006	90	71	95	77	82	92	B	
21	Nike	One Platinum (08)	2008	107	88	105	87	77	87	S	
22	Nike	One Black (08)	2008	100	81	97	79	80	90		
23	Nike	One Platinum (07)	2007	101	82	102	84	76	86	D	
24	Nike	One Black (07)	2007	102	83	101	83	80	90	A	
25	Nike	One Platinum (06)	2006	97	78	102	84	77	87	T	
26	Nike	One Black (06)	2006	109	90	102	84	78	88	A	
27	Nike	Ignite (07)	2007	87	68	89	71	87	97	B	
28	Nike	Ignite (06)	2006	86	67	88	70	78	88	A	
29	Nike	Power Distance Soft (08)	2008	70	51	74	56	84	94	S	
30	Noodle	Noodle + (08)	2008	75	56	78	60	86	96	E	
31	Pinnacle	Ribbon (08)	2008	86	67	88	70	88	98		
32	Pinnacle	Platinum Distance (08)	2008	85	66	86	68	87	97		
33	Pinnacle	Platinum Feel (08)	2008	81	62	80	62	83	93		
34	Pinnacle	Exception (06)	2006	78	59	79	61	86	96		
35	Precept	Distance IQ 180 (08)	2008	70	51	78	60	86	96		
36	Precept	Lady IQ 180 (08)	2008	67	48	68	50	86	96		
37	Srixon	Z-URC (07)	2007	110	91	102	84	85	95		
38	Srixon	Ladies Soft Feel (08)	2008	75	56	75	57	87	97		
39	Srixon	Soft Feel (06)	2006	75	56	81	63	85	95		
40	Srixon	AD333 (07)	2007	78	59	78	60	83	93		
41	Srixon	AD333 (06)	2006	82	63	86	68	81	91		
42	Srixon	Trispeed (07)	2007	69	50	73	55	85	95		
43	Srixon	Z-URS (07)	2007	98	79	95	77	81	91		
44	Srixon	Z-URS (06)	2006	100	81	102	84	83	93		
45	Srixon	Z-UR (06)	2006	110	91	111	93	85	95		
46	TaylorMade	Burner (08)	2008	77	58	73	55	86	96		
47	TaylorMade	Burner TP (08)	2008	87	68	89	71	81	91		
48	TaylorMade	TP Red (08)	2008	95	76	92	74	80	90		
49	TaylorMade	TP Black (08)	2008	117	98	115	97	80	90		
50	TaylorMade	TP Red (06)	2006	111	92	106	88	81	91		
51	TaylorMade	TP Black (06)	2006	117	98	110	92	82	92		



**Compression and Cover
Hardness Ratings**

MPI™ Data Sheet

Release Date: 4/19/2008

				Overall Compression				Cover Hardness			
				Majestix		Atti		Teclock Type C			
	Manufacturer	Model	Year		Avg	MPI™	Avg	MPI™		Avg	MPI™
52	Titleist	Pro V1 (07)	2007		93	74	95	77		78	88
53	Titleist	Pro V1 (06)	2006		97	78	99	81		76	86
54	Titleist	Pro V1x (07)	2007		103	84	100	82		79	89
55	Titleist	Pro V1x (06)	2006		110	91	114	96		78	88
56	Titleist	NXT Extreme (07)	2007		76	57	82	64		88	98
57	Titleist	NXT (06)	2006		73	54	77	59		88	98
58	Titleist	NXT Tour (07)	2007	G	88	69	92	74	G	81	91
59	Titleist	NXT Tour (06)	2006	B	88	69	88	70	B	80	90
60	Titleist	DT Roll (08)	2008	S	87	68	90	72	S	83	93
61	Titleist	DT Carry (08)	2008		79	60	79	61		80	90
62	Titleist	DT SoLo (06)	2006	D	79	60	78	60	D	84	94
63	Top Flite	D2 Straight (07)	2007	A	77	58	77	59	A	87	97
64	Top Flite	D2 Feel (07)	2007	T	71	52	74	56	T	85	95
65	Top-Flite	Freak (08)	2008	A	87	68	88	70	A	90	100
66	Top-Flite	Gamer (08)	2008	B	98	79	95	77	B	83	93
67	Volvik	PROs Pect (07)	2007	A	81	62	81	63	A	86	96
68	Wilson	Tx4 Tour (06)	2006	S	109	90	105	87	S	82	92
69	Wilson	Fifty (07)	2007	E	75	56	72	54	E	83	93
70	Wilson	Zip (07)	2007		68	49	67	49		83	93
71	Wilson	TX4 Pro (08)	2008		119	100	118	100		84	94
72	Wilson	Hope (07)	2007		81	62	84	66		88	98
73	Wilson	DX2 Distance (06)	2006		85	66	83	65		85	95
74	Wilson	PX3 Performance (06)	2006		80	61	84	66		82	92

Technical Notes:

1. Compression tests performed measuring overall golf ball compression using the Majestix and Atti compression test devices. The higher the number, the less the ball compresses when subjected to a force.
2. Cover hardness tests performed measuring golf ball surface hardness using a Teclock Type C durometer test device in accordance with ASTM D 2240 C.
3. The MPI™ ratings are based on a 100 point scale where for compression the higher the number the firmer the golf ball and for cover hardness the higher the number the firmer the golf ball.
3. The average compression and cover hardness data were calculated after a statistically significant number of data points per golf ball were collected using systematic test procedures.
4. The golf balls were acquired independent of manufacturers.

